BULLCREM LACK
POWDER COATINGS
SAVID
STABILIMENTO E SEDE LEGALE
Via del Lavoro, 20 - 31039 Riese Pio X (TV) - Italy
Tel: +39 0423 755 547 - www.bullcrem-lack.com

ISO 9001 BUREAU VERITAS Certification

PRODUCT TECHNICAL DATA SHEET

Edition: 02/2026

CODE: **MLI130000003** | DESIGNATION: **MPE ROSSO FASS 50396**

Product Description

Thermosetting powder coating based on saturated polyester and epoxy resins, additives, and selected pigments, specifically for indoor applications.

Fields of Use

Metal products for indoor use not exposed to UV rays.

Chemical-Physical Characteristics of the Powder

- **Surface Appearance:** Smooth / Gloss
- **Color:** Red 3000
- **Gloss (60°):** 85 – 95 glosses
- **Theoretical Density:** 1.40 - 1.65 g/cm³
- **Average Particle Size (d50):** 35 - 45 µm (LASER spectrometry method)
- **Fluidity (SAMES):** > 140
- **Storage and Stability:** 6 months in original sealed packaging, stored in a dry environment at a temperature < 30°C and protected from heat sources/direct light.

Theoretical Consumption Calculation:

Consumption (g/m²) = Average Specific Gravity (g/cm³) × Required Thickness (µm)

Coating Performance (Test Conditions)

All application tests are performed under standardized laboratory conditions. Mechanical tests are conducted on AA 5005-H24 aluminium alloy panels (thickness 0.8 - 1.0 mm). Corrosion tests are conducted on AA 6060 alloy panels with a dry film thickness requirement (60 - 80 µm).

1. Mechanical and Adhesion Properties

Test / Property	Reference Standard	Requirement / Result
Adhesion (Cross-Cut)	EN ISO 2409 (2 mm pitch)	Gt0 (No detachment)
Erichsen Cupping Test	EN ISO 1520	PASS ≥ 5 mm
Impact Resistance	EN ISO 6272-2 / ASTM D2794	PASS 2,5 Nm (Indirect Impact, indenter Ø 15,9 mm)
Pencil Hardness	EN ISO 15184	H – 2H

2. Chemical, Corrosion and Weathering Resistance

Test / Property	Reference Standard	Specifications and Acceptance Limits
Salt Spray (AASS)	EN ISO 9227	500 hours → Blistering ≤ S2 (ISO 4628-2); max infiltration ≤ 1 mm per side
Moisture Resistance	EN ISO 6270-2	500 hours (Humidity chamber) → No macroscopic alterations; blistering ≤ S2 (ISO 4628-2)

STABILIMENTO E SEDE LEGALE
Via del Lavoro, 20 - 31039 Riese Pio X (TV) - Italy
Tel: +39 0423 755 547 - www.bullcrem-lack.com

Curing Specifications (Effective object temperature)

- **180°C:** 20 – 30 minutes

Technical Notes: In case of using gas-fired direct-flame ovens, please contact our technical support service in advance.

Application Guidelines

- **Surface Preparation:** The metallic substrate must undergo industrial degreasing and deoxidizing cycles. To maximize outdoor corrosion resistance, the application of a suitable chemical conversion treatment.
- **Spraying Techniques:** Suitable for application with automatic or manual electrostatic systems, using both Corona and Tribo charging methods.
- **Compatibility:** Do not mix this product with powder coatings of a different nature or different batches to avoid contamination, gloss reduction, or cratering phenomena.
- **Powder Recycling:** For solid colors, the powder can be recovered and recycled into the coating system, but it is necessary to use at least 70% virgin powder.
- **Safety:** Product for professional use only; consult the relevant Safety Data Sheet (SDS).

Legal Notes & Disclaimer

The information provided in this technical data sheet reflects the current state of our knowledge and results from rigorous laboratory testing. The data refer exclusively to the materials described and do not exempt the user from performing preventive checks on their own production line in relation to specific process variables. We reserve the right to modify technical data without prior notice within the framework of continuous product improvement.