



**BULLCREM LACK**

POWDER COATINGS

MANUFACTURING PLANT &  
REGISTERED OFFICE  
Via del Lavoro, 20  
31039 Riese Pio X (TV) – Italia  
Tel.: +39 0423 755 547

## Technical Data Sheet

Version No. 2/2022

### **PLI270160002 PES IND GRIGIO SL 65G 7016**

Thermosetting powder coating with specifically selected resins, additives and pigments providing outstanding general properties; suitable for outdoor decorative applications where a high outdoor resistance is not required.

#### **Fields of application**

Garden furniture, lighting systems, road signposts and other metal items for indoor/outdoor use.

#### **Technical specifications**

Surface appearance: Smooth

Color: Grey

Substrate: Iron/Steel

Density: 1.45-1.55 g/cm<sup>3</sup>

Polymerization condition: 180°C X 8 - 15min

(actual on the piece) 160°C X 10 - 20min

Gloss (60°): 65 +/- 5

ISO 2813

Theoretical yield: multiply the average of the specific gravity by the requested thickness in microns.  
The obtained value is the consumption in grams per square meters

#### **Particle size distribution**

The average particle size (d50) of powder coatings determined using the LASER method is normally between 35 and 45 microns. Special particle size distributions are available upon request, depending on the needs.

The characteristics of the product, such shine, colour and finishing may vary based on the application and polymerization conditions.

Please feel free to contact us, should you use it in direct flame polymerization furnaces.



Bullcrem Lack Srl

VAT Tax payer and Company Registration No. TV 03951000243 – Treviso Economic and Administrative Database No. 373595 – Fully paid up capital Euro 500,000.00  
Company subject to management and coordination by Managlio Srl  
E-mail: info@bullcrem-lack.com – Registered e-mail bullcrem-lack@pec-easy.it



BULLCREM LACK

POWDER COATINGS

## Technical Data Sheet

Version No. 2/2022

MANUFACTURING PLANT &  
REGISTERED OFFICE  
Via del Lavoro, 20  
31039 Riese Pio X (TV) – Italia  
Tel.: +39 0423 755 547

### Chemical-physical characteristics

All tests were carried out in a laboratory under controlled standard conditions, using panels made from an AA 5005-H24 alloy for mechanical tests; while corrosion tests were carried out on AA 6060 alloy panels.

### Mechanical tests:

Deep drawing ISO 1520 - PASS 5mm

Bending ISO 1519 - PASS 5mm

Impact resistance ISO 6272 - PASS 2.5Nm

Pencil hardness ISO 15184 - H-2H

### Chemical/corrosion resistance:

Humidistat and immersion trials in distilled water: no blistering and loss of shine

Good resistance to acids, alkalis and oils at normal temperatures

### Preparation of the surface

Thoroughly remove grease, processing residues and rust from the item.

A suitable chemical conversion is recommended to achieve a good level of protection against corrosion before coating.

### Application

Do not mix this product with other powders in order to avoid possible incompatibility problems. For metallic effect powders we suggest to work on a spray-to-waste basis as their metallization is obtained by means of a dry-blend process of components with different chromatic aspects and specific weights. As a result of different coating processes and, if any, of overspray recycling methods, the final metallic effect might present substantial differences in colour and aspect from the initial standard.

For all metallic effect powders the corona application is recommended.

Metallic effect coatings are generally not scratch resistant. We recommend to handle such objects with care.

We recommend a film thickness between 60 and 90 microns. For yellow, orange and red coatings a film thickness between 100 and 120 microns is recommended.



BULLCREM LACK  
POWDER COATINGS

Bullcrem Lack Srl

VAT payer and Company Registration No. TV 03951000243 – Treviso Economic and Administrative Database No. 373595 – Fully paid up capital Euro 500,000.00

Company subject to management and coordination by Managlio Srl

E-mail: info@bullcrem-lack.com – Registered e-mail bullcrem-lack@pec-easy.it



BULLCREM LACK

POWDER COATINGS

## Technical Data Sheet

Version No. 2/2022

MANUFACTURING PLANT &  
REGISTERED OFFICE  
Via del Lavoro, 20  
31039 Riese Pio X (TV) – Italia  
Tel.: +39 0423 755 547

---

### Storage

The product stored in a dry place at a temperature below 30°C stays stable for at least 24 months..

The information hereby provided is the result of our experience and shall be subject to review. Data provided fall within the normal scope of the product characteristics and refer to specific materials only. Bullcrem Lack may not foresee all the variations to the final use, hence they can not provide any guarantee and shall accept no responsibility connected to the use of the aforementioned information.

The information contained in the present sheet is subject, without notice, to modifications for the continuous improvement of the product. For special information please feel free to contact our laboratory technicians.



Bullcrem Lack Srl

VAT, Tax payer and Company Registration No. TV 03951000243 – Treviso Economic and Administrative Database No. 373595 – Fully paid up capital Euro 500,000.00



Company subject to management and coordination by Managlio Srl  
E-mail: info@bullcrem-lack.com – Registered e-mail bullcrem-lack@pec-easy.it